

COLONIAL flooring range

Our "Colonial" floor is made from bamboo strips flattened according to a special process, giving it the genuine look of the bamboo cane. The planks are finished in factory with a wax oil. The quality of our products allows us to offer a guarantee up to 30 years provided that the installation is done according to our instructions, respecting the standards in force in the country and following our maintenance recommendations.



Colonial

Reference	Coating	Color	Glued pose	Floating pose	Floor-heating ³	Bath-room ³	Dimensions (mm)	Wear layer	Structure	Bevel	Inter-locking ²	Content box
F18CBBR125	Waxed	Brown maroon	✓	✓	✓	✓	18x97/125x1210	±6	Massif	GO4	T/G	1,61m ² 22kg

² R/L = Tongue/Groove

³ Installation on heated floor and in bathrooms **must be glued**.

Installation advice available on our website www.bambootouch.com/en/advice.

Storage, installation and maintenance (DTU 51.2 or local standard)

- Planks should be stored horizontally at a temperature of 15 to 25°C and relative humidity of 45 to 65 %.
- The flooring requires acclimatization and will be left 48h in its open packaging on the place of installation.
- Bamboo is a natural product. Variations in color, grain or shine are normal. Be sure to mix the planks from different packages before installation. **All installed flooring will be considered accepted.**
- The screed must be dry, clean and even. The moisture content, evenness and load-bearing capacity of the screed must be in accordance with current standards. Residual moisture must not exceed 2.7%.
- Allow for an expansion gap of +/- 1 cm around the floor and obstacles.
- Provide a divider joint every 8 to 10m.
- Installation, cleaning and maintenance instructions are available on our website www.bambootouch.com/en/advice.

Caractéristiques techniques

- Brinell hardness: ±4,3 kg/mm² (EN 1534 – CTIB 5229/2)
- Contraction coefficient: 0,14% per % of humidity variation
- Humidity level : 10% at 20° and 65% of relative humidity
8% at 20° and 50% of relative humidity
- Density : ±740 kg/m³
- Fire standard : CFLS1 if glued pose (BFLS1 for some products)
- Formaldehyde emissions: 0,04mg/m²h (EN 717-2 CTIB 5229/2)
- PCP level : below detection limit (CTIB 5229/2)
- VOC Free : below detection limit (EN15052 CTIB 5229/2)
- Thermal resistance : 0,05m²K/W (EN12664 CTIB 5229/2)
- Thermal conductivity : 0,20W/mK
- Warranty: up to 30 years under conditions (see our website)

Don't forget the accessories !