BAMBCOTouch®

Flooring BAMWOOD® range

Our "BamWood®" flooring is made from bamboo strips assembled under very high pressure, giving it a noble and elegant appearance. The planks are finished in the factory, either with a UV varnish with a matt appearance or with Woca® oil, also with a matt appearance. The quality of our products allows us to offer a warranty of up to 30 years on condition that the installation is done according to our instructions, respecting the norms in effect in the country and following our maintenance recommendations.





Gold







Nairobi Corfou

Reference	Coating ¹	Color	Glued pose	Floating pose	Floor heating ³	Bath- room³	Dimensions (mm)	Wear layer (mm)	Structure	Bevel	Inter- locking ²	Content box
F10BCC60	V	Caramel	✓	√	✓	✓	10x60x920	±4	Solid	GO2	T/G	1,77m² 18kg
F10BIC200	В	Caramel	✓	Χ	✓	✓	10x200x300	±5	Solid	-	-	1,92m² 19kg
F10BCC130	V	Caramel	√	✓	√	√						
F10BOC130	Н	Caramel	\checkmark	\checkmark	\checkmark	\checkmark						
F10BCCH130	V	Champagne	\checkmark	✓	\checkmark	\checkmark	10x130x915	±4	Solid	GO2	T/G	1,9m² 19kg
F10BOCH130	Н	Champagne	\checkmark	\checkmark	\checkmark	\checkmark						
F10BCG130	V	Gold	\checkmark	\checkmark	\checkmark	\checkmark						
F10BOCBR95	Н	Caramel	✓	Χ	✓	✓	10x95x855	±4	Solid	GO2	T/G	1,95m² 20kg
F10B0CHBR122	Н	Champagne	\checkmark	Χ	\checkmark	\checkmark	10x122x610					1,79m² 21kg
F10BCCL125	V	Caramel	Χ	✓	Χ	Χ						
F10BCHCL125	V	Champagne	Χ	\checkmark	Χ	X	10x125x920	±2,5	HDF	GO2	Click	1,38m² 12kg
F10BGCL125	V	Gold	Χ	\checkmark	Χ	X						
F14BMCCL190	V	Caramel	✓	✓	✓	√						
F14BMCCHCL190	V	Champagne	\checkmark	\checkmark	\checkmark	\checkmark	14x190x1850	±3	Multiply	GO2	Click	2,11m ² 17kg
F14BMGCL190	V	Gold	\checkmark	\checkmark	\checkmark	\checkmark						
F12BCC142	V	Caramel	√	√	√	√						
F12BOCH142	Н	Champagne	\checkmark	\checkmark	\checkmark	\checkmark	12x142x1850		C = 1: -1	603	TIC	2.12.251
F12BCG142	V	Gold	\checkmark	\checkmark	\checkmark	\	12X142X1850	±4	Solid	GO2	T/G	2,1m ² 25kg
F12BCNA142	V	Nairobi	\checkmark	\checkmark	\checkmark	\checkmark						
F14BMCC142	V	Caramel	✓	√	✓	✓						
F14BMCCH142	V	Champagne	\checkmark	\checkmark	\checkmark	✓	14x142x1850	±3	Multiply	GO2	T/G	2,1m ² 21kg
F14BMCG142	V	Gold	\checkmark	\checkmark	\checkmark	V						· ·
F14BMOC208	Н	Caramel	✓	✓	✓	✓	14 200 4050		8.4. It's L.	602	T/C	2.24 2.25
F14BMOCH208	Н	Champagne	\checkmark	\checkmark	\checkmark	✓	14x208x1850	±3	Multiply	G02	T/G	2,31m ² 25kg
F13BOCO140	Н	Corfou	✓	✓	V	✓	13x140x1850	±3	3 crossed layers bb	GO2	T/G	2,07m² 27kg
F13BONA140 F13BCNA140	H V	Nairobi Nairobi	✓ ✓	✓	✓ ✓	√ √	13x140x1850	±3	3 crossed layers bb	GO2	T/G	2,07m² 27kg

 $^{^{1}}$ V= varnish/ H= Oil / B= Unfinished - 2 T/G = Tongue/Groove - 3 Installation on heated floor and in bathrooms must be glued.

Installation advice available on our website www.bambootouch.com/en/advice.

Storage, installation and maintenance (DTU 51.2 or local standard)

- Planks should be stored horizontally at a temperature of 15 to 25°C and relative humidity of 45 to 65 %.
- The flooring requires acclimatization and will be left 48h in its open packaging on the place of installation.
- Bamboo is a natural product. Variations in color, grain or shine are normal. Be sure to
 mix the planks from different packages before installation. All installed flooring will
 be considered accepted.
- The screed must be dry, clean and even. The moisture content, evenness and loadbearing capacity of the screed must be in accordance with current standards. Residual moisture must not exceed 2.7%.
- Allow for an expansion gap of +/- 1 cm around the floor and obstacles.
- Provide a divider joint every 8 to 10m.
- Splits and fiber separation are possible on oiled products. This phenomenon is natural
 and is no reason for warranty claim. A (light) sanding and oiling will reduce them.
- Blanchon[®] oil is not compatible with our oiled floorings.
- Installation, cleaning and maintenance instructions are available on our website www.bambootouch.com/en/advice.

Technical specifications

- Brinell hardness: ±9 kg/mm² (EN 1534 CTIB 5229/2)
- Contraction coefficient: 0,14% per % of humidity variation
- Humidity level: 10% at 20° and 65% of relative humidity
 8% at 20° and 50% of relative humidity
- Density: ±1.050 kg/m³
- Fire standard : CFLS1 if glued pose BFLS1 for some products
- Formaldehyde emissions: 0,04mg/m²h (EN 717-2 CTIB 5229/2)
- PCP level: below detection limit (CTIB 5229/2)
- VOC Free : below detection limit (EN15052 CTIB 5229/2)
- Thermal resistance : 0,05m²K/W (EN12664 CTIB 5229/2)
- Thermal conductivity: 0,20W/mK
- Warranty: up to 30 years under conditions (see our website)

nv Pi-Import sa

Av du Commerce 33 1420 Braine-l'Alleud – Belgium Tel. : +32 (0)2 384 58 77















info@bambootouch.com www.bambootouch.com