



## Flooring HORIZONTAL range

Our "Horizontal" flooring is made from horizontally assembled bamboo strips, giving it a natural and Zen look. The strips are finished in factory with a UV varnish of matt aspect. The quality of our products allows us to offer a guarantee of up to 30 years provided that the installation is done according to our instructions, respecting the standards in force in the country and following our maintenance recommendations.



Naturel



Caramel

Reference	Coating <sup>1</sup>	Color	Glued pose	Floating pose	Floor-heating <sup>3</sup>	Bath-room <sup>3</sup>	Dimensions (mm)	Wear Layer (mm)	Structure	Bevel	Inter-locking <sup>2</sup>	Content box
F10HCC96	V	Caramel	✓	X	✓	✓	10x96x980	±4	2 crossed Layers bb	GO2	T/G	3,39m² 24kg
F15HCC130	V	Caramel	✓	✓	✓	✓	15x130x1020	±5	3 crossed Layers bb	GO2	T/G	2,12m² 21kg
F15HCN150	V	Naturel	✓	✓	✓	✓	15x150x1940	±5	3 crossed Layers bb	GO2	T/G	2,33m² 25kg

<sup>1</sup> V= varnish / H= oil

<sup>2</sup> T/G = Tongue/Groove

<sup>3</sup> Installation on heated floor and in bathrooms **must be glued**.

Installation advice available on our website [www.bambootouch.com/en/advice](http://www.bambootouch.com/en/advice).

### Storage, installation and maintenance (DTU 51.2 or local standard)

- Planks should be stored horizontally at a temperature of 15 to 25°C and relative humidity of 45 to 65 %.
- The flooring requires acclimatization and will be left 48h in its open packaging on the place of installation.
- Bamboo is a natural product. Variations in color, grain or shine are normal. Be sure to mix the planks from different packages before installation. **All installed flooring will be considered accepted.**
- The screed must be dry, clean and even. The moisture content, evenness and load-bearing capacity of the screed must be in accordance with current standards. Residual moisture must not exceed 2.7%.
- Allow for an expansion gap of +/- 1 cm around the floor and obstacles.
- Provide a divider joint every 8 to 10m.
- Installation, cleaning and maintenance instructions are available on our website [www.bambootouch.com/en/advice](http://www.bambootouch.com/en/advice).

### Caractéristiques techniques

- Brinell hardness: ±4,3 kg/mm² (EN 1534 – CTIB 5229/2)
- Contraction coefficient: 0,14% per % of humidity variation
- Humidity level : 10% at 20° and 65% of relative humidity  
8% at 20° and 50% of relative humidity
- Density : ±740 kg/m³
- Fire standard : CFLS1 if glued pose (BFLS1 for some products)
- Formaldehyde emissions: 0,04mg/m²h (EN 717-2 CTIB 5229/2)
- PCP level : below detection limit (CTIB 5229/2)
- VOC Free : below detection limit (EN15052 CTIB 5229/2)
- Thermal resistance : 0,05m²K/W (EN12664 CTIB 5229/2)
- Thermal conductivity : 0,20W/mK
- Warranty: up to 30 years under conditions (see our website)

**Don't forget the accessories !**