

Flooring VERTICAL range

Our "Vertical" flooring is made from vertically assembled bamboo strips, giving it a contemporary and refined look. The planks are finished in the factory, either with a UV varnish with a matte appearance or with a Woca® oil with a matte appearance. The quality of our products allows us to offer a guarantee of up to 30 years provided that the installation is done according to our instructions, respecting the standards in force in the country and following our maintenance recommendations.



Naturel




Champagne



Gold



Caramel



Caramel Navy

Reference	Coating ¹	Color	Glued pose	Floating pose	Floor-heating ³	Bath-room ³	Dimensions (mm)	Wear Layer (mm)	Structure	Bevel	Inter-locking ²	Content box
F10VIC140	B	Caramel	✓	X	✓	✓	10x140x280	±5	Solid	-	-	2,67m ² 21kg
F12VCC96	V	Caramel	✓	✓	✓	✓	12x96x960	±4,4	Solid	GO2	R/L	2,76m ² 23kg
F12VOCH96	H	Champagne	✓	✓	✓	X						
F12VCG96	V	Gold	✓	✓	✓	✓						
F12VOC96	H	Caramel	✓	✓	✓	X						
F15VCNA96	V	Caramel Navy	✓	✓	✓	✓	15x96x2020	±5	Sokid	GO2	R/L	2,33m ² 24kg
F10VCC128	V	Caramel	X	✓	X	X	10x128x960	±2,5	HDF	GO2	Click	1,47m ² 14,4kg
F15VCC150	V	Caramel	✓	✓	✓	✓	15x150x1940	±5	3 crossed Layers bb	GO2	R/L	2,33m ² 24kg
F15VCN150	V	Naturel	✓	✓	✓	✓						
F15VOC150	H	Caramel	✓	✓	✓	X						
F15VCC190	V	Caramel	✓	✓	✓	✓	15x190x2200	±4	Multiply	GO2	R/L	3,34m ² 26kg
F15VCG190	V	Gold	✓	✓	✓	✓						
F15VOCH190	H	Champagne	✓	✓	✓	X						

¹ V= varnish / H= oil

² T/G = Tongue/Groove

³ Installation on heated floor and in bathrooms **must be glued**.

Installation advice available on our website www.bambootouch.com/en/advice.

Storage, installation and maintenance (DTU 51.2 or local standard)

- Planks should be stored horizontally at a temperature of 15 to 25°C and relative humidity of 45 to 65 %.
- The flooring requires acclimatization and will be left 48h in its open packaging on the place of installation.
- Bamboo is a natural product. Variations in color, grain or shine are normal. Be sure to mix the planks from different packages before installation. **All installed flooring will be considered accepted.**
- The screed must be dry, clean and even. The moisture content, evenness and load-bearing capacity of the screed must be in accordance with current standards. Residual moisture must not exceed 2.7%.
- Allow for an expansion gap of +/- 1 cm around the floor and obstacles.
- Provide a divider joint every 8 to 10m.
- Installation, cleaning and maintenance instructions are available on our website www.bambootouch.com/en/advice.

Caractéristiques techniques

- Brinell hardness: ±4,3 kg/mm² (EN 1534 – CTIB 5229/2)
- Contraction coefficient: 0,14% per % of humidity variation
- Humidity level : 10% at 20° and 65% of relative humidity
8% at 20° and 50% of relative humidity
- Density : ±740 kg/m³
- Fire standard : CFLS1 if glued pose (BFLS1 for some products)
- Formaldehyde emissions: 0,04mg/m²h (EN 717-2 CTIB 5229/2)
- PCP level : below detection limit (CTIB 5229/2)
- VOC Free : below detection limit (EN15052 CTIB 5229/2)
- Thermal resistance : 0,05m²K/W (EN12664 CTIB 5229/2)
- Thermal conductivity : 0,20W/mK
- Warranty: up to 30 years under conditions (see our website)

Don't forget the accessories !

nv Pi-Import sa

Av du Commerce 33

1420 Braine-l'Alleud – Belgium

Tel. : +32 (0)2 384 58 77

Technical file Vertical flooring

info@bambootouch.com

www.bambootouch.com
