



BambooTouch® iDecKing® composite decking is made from 60% sawdust, 30% recycled high-density polyethylene (HDPE) and 10% additives (UV stabilizers, antioxidants, binders and hardeners, stabilizers, colorants). The components are mixed under high pressure, resulting in very dense, rot-proof and durable blades. The quality of our products enables us to offer a warranty of up to 10 years, provided that installation is carried out according to our instructions, in compliance with local regulations, using our accessories (joists, etc.) and following our cleaning recommendations.



Old Brown

Light Grey

Sand

Keel Alu A et B

Profile Old Brown

Profile Light Grey

Profile Sand

Reference	Type	Color	Dimensions mm)	Sides	Installation	Quantity/palet
D20CIOB137	Plank	Old Brown	20x137x2200	1 side old wood	Clic	144 planks 43,4m ²
D20CILG137	Plank	Light Grey	20x137x2200	1 side wood	Clic	144 planks 43,4m ²
D20CISA137	Plank	Sand	20x137x2200	1 plain	Clic	144 planks 43,4m ²
IDCL140203	Alu keel type A		20x60x2030			448 pcs
IDCF140203	Alu keel type B		20x60x2030			448 pcs
DPRFINOB	Finishing profile	Old Brown	20x53/47x2200	Plain	Click	300 pcs
DPRFINLG	Finishing profile	Light Grey	20x53/47x2200	Plain	Click	300 pcs
DPRFINS	Finishing profile	Sand	20x53/47x2200	Plain	click	300 pcs

Storage, installation and maintenance (conform DTU 51.4 of local standards)

- The planks should be stored horizontally.
- A correctly dimensioned sub-structure (studs, keels) must be installed in accordance with current standards.
- The structure must be naturally ventilated (>1% of the surface)
- Since the main component is natural, there may be slight color differences between different batches. Be sure to mix the planks well before installation.
- Our planks, keels and profiles are guaranteed. We do not guarantee the use of other accessories or fixing materials (keels, battens, etc.)
- The use of iDecKing aluminium keels is essential.
- Cleaning should be carried out at least once a year.
- Installation and cleaning instructions are available on our website.
Installation : www.bambootouch.com/en/conseils
Cleaning : www.bambootouch.com/en/conseils

Technical data

- Brinell hardness: ±52 N/mm² structured side
±86,7 N/mm² plain side (TFI 42135-04)
- Density: ±1340 kg/m³
- Humidity level : 2,6% (28d immersion at 20°C)
- Fire standard : DFL-S1 EN13893 – TFI 421335-05 – EN13501-1:2010
- Thermal resistance : Flammability ISO11925-2 :2010 standards
- Modular elasticity : 23,4 N/mm²
- Dimensional stability: width max : 0,3% (28 d immersion at 20°C)
length max : 0,2% (28 d immersion at 20°C)
thickness max : 2% (28 d immersion at 20°C)
- Slip resistance : DS class. Coefficient of friction μ : 0,31 in length and 0,40 in width(EN13893 :2002, TFI 421335-07)
- Warranty : 10 year as by conditions (cfr our website)